

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 924 109 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
23.06.1999 Bulletin 1999/25

(51) Int. Cl.⁶: B60C 17/00, B60C 9/14,
B60C 9/00

(21) Application number: 98310603.0

(22) Date of filing: 22.12.1998

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 22.12.1997 JP 35376697


(71) Applicant:
BRIDGESTONE CORPORATION
Tokyo 104-0031 (JP)

(72) Inventors:
• Nishikawa, Tomohisa,
c/o Bridgestone Corporation
Chuo-ku, Tokyo 104-0031 (JP)
• Matsuo, Kenji,
c/o Bridgestone Corporation
Chuo-ku, Tokyo 104-0031 (JP)
• Kobayashi, Kazuomi,
C/o Bridgestone Corporation
Chuo-ku, Tokyo 104-0031 (JP)

(74) Representative: Whalley, Kevin
MARKS & CLERK,
57-60 Lincoln's Inn Fields
London WC2A 3LS (GB)

(54) Pneumatic tire for passenger cars

(57) The present invention provides a pneumatic tire for passenger cars comprising bead cores, a carcass layer, a tread portion, and side wall portions, wherein a rubber reinforcing layer having a crescent-shaped cross-section and at least one sheet of a rubber-filament fiber composite having a thickness measured under a pressure of 20 g/cm² of 0.05 to 2.0 mm which is formed from a rubber component and filaments having a diameter or a maximum cross-sectional dimension of 0.0001 to 0.1 mm and a length of 8 mm or more are disposed in said side wall portions and reinforcing cords of carcass plies are made of an aliphatic polyamide fiber having a melting point of 250°C or higher. Deterioration of adhesion in carcass ply does not take place during use, particularly during use in a run-flat condition, and the pneumatic tire shows excellent durability.



EP 0 924 109 A2

Description

BACKGROUND OF THE INVENTION

5 Field of the Invention

[0001] The present invention relates to a pneumatic tire for passenger cars, and more particularly to a pneumatic tire for passenger cars which shows excellent durability and can be safely used even when the internal pressure of the tire is reduced.

10

Description of the Related Art

[0002] Cords of aliphatic polyamide fibers such as nylon 66 fiber are frequently used as reinforcing cords for tires because of their high strength and excellent resistance to wear. However, these cords do not always give satisfactory results when they are used for pneumatic tires for passenger cars.

15

[0003] Pneumatic tires for passenger cars have been improved remarkably in recent years by the use of cords of polyester fibers which show excellent dimensional stability and have high strength in place of the above fibers for reinforcement of the tires.

[0004] Among the polyester fibers, polyethylene terephthalate fibers (PET) are generally used as the reinforcing material for rubber such as tire cords because PET has a Young's modulus higher than that of nylon 66 fiber and about the same as that of rayon and shows a better balance of physical properties than other fiber materials.

20

[0005] However, PET shows inferior dimensional stability under heating because of a decrease in the Young's modulus although PET shows a relatively high Young's modulus at room temperature. Therefore, in spite of the high Young's modulus, PET manufactured to suit industrial applications such as the reinforcement of rubber has a drawback in that the Young's modulus decreases under heating to about the same value as that of general use PET used for clothing.

25

[0006] Polyethylene naphthalate fibers (PEN) stretched sufficiently by a heat treatment show a Young's modulus almost twice that of PET at room temperature. Moreover, PEN has a Young's modulus as high as 100 g/d or more at 100°C or higher and shows excellent dimensional stability under heating such as a dry heat shrinkage of 2% or less at 150°C. Therefore, the application of PEN as the reinforcing material of rubber such as tire cords has been attempted.

30

[0007] However, heat buildup inside a tire is extremely large when the tire is used with a lower internal pressure, i.e., under so-called run-flat conditions. Therefore, adhesion at high temperatures is not sufficient even when PET or PEN is used. The main cause of failure of a tire during use in a run-flat condition is separation at the interface of the PET or PEN and the adhesive layers.

35 SUMMARY OF THE INVENTION

[0008] The object of the present invention is to provide a pneumatic tire for passenger cars which shows excellent durability because separation at the interfaces of adhesive layers and reinforcing fibers does not take place during use, particularly during use in a run-flat condition, and a layer of a rubber-filament fiber composite is disposed at side wall portions of the tire.

40

[0009] As the result of studies in detail by the present inventors on the behavior of carcass plies when used in a run-flat condition, it was found that a pneumatic tire for passenger cars showing an excellent durability can be provided when a specific aliphatic polyamide is used for the reinforcing cords and a rubber-filament fiber composite is disposed at the side wall portions. The present invention has been completed based on the above knowledge.

45

[0010] The present invention provides a pneumatic tire for passenger cars comprising:

a pair of left and right bead cores;

a carcass formed from layer in which a plurality of reinforcing cords disposed parallel to each other are embedded in a coating rubber;

50

a tread portion disposed at an outer side of the carcass portion in the radial direction of the tire; and

a pair of side wall portions disposed at the left and right of the tread portion;

wherein a rubber reinforcing layer having a crescent-shaped cross-section and at least one sheet of a rubber-filament fiber composite having a thickness of 0.05 to 2.0 mm which is formed from a rubber component and filament fibers having a diameter or a maximum cross-sectional dimension of 0.0001 to 0.1 mm and a length of 8 mm or

55

more are disposed in the side wall portions; and

the reinforcing cord of carcass ply is made of an aliphatic polyamide fiber having a melting point of 250°C or higher as measured by DSC.

[0011] It is preferable that the filament fiber in the rubber-filament fiber composite is a fiber selected from the group consisting of aromatic polyamide fiber, rayon fiber, polyethylene naphthalate fiber, polyimide fiber, carbon fiber, glass fiber and steel wire, that the filament fiber in the rubber-filament fiber composite has a diameter or a maximum cross-sectional dimension of 0.0001 to 0.005 mm and a length of 10 mm or more, that the content of the filament fiber in said rubber-filament fiber composite is 4 to 50% by weight, that said rubber-filament fiber composite is formed from a rubber and a nonwoven fabric having a weight per area of 10 to 300 g/m², that said nonwoven fabric has a thickness of 0.1 to 0.5 mm and that said reinforcing cord of carcass ply is made of nylon 66 fiber or nylon 46 fiber.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012]

Fig. 1 shows a schematic cross sectional view of an example of the pneumatic safe tire of the present invention.

Fig. 2 shows a schematic cross sectional view of another example of the pneumatic safe tire of the present invention.

Fig. 3 shows schematic presentations of the structures of a side portion (a carcass portion) of the pneumatic safe tire used as an example of the present invention and as a comparative example.

Fig. 4 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 5 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 6 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 7 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 8 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 9 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 10 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 11 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 12 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 13 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 14 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 15 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

Fig. 16 shows a schematic presentation of the structure of a side portion (a carcass portion) of the pneumatic safe tire used in another example of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0013] The reinforcing cord of the carcass ply of the pneumatic tire for passenger cars of the present invention is made of an aliphatic polyamide fiber having a melting point of 250°C or higher as measured by DSC. By the use of this fiber, strong adhesion between rubber parts and the fiber can be obtained even at high temperatures and deterioration of the adhesion in carcass ply can be prevented.

[0014] A stabilizer such as a stabilizer comprising a copper salt and an antioxidant may be added to the polyamide fiber in order to provide the fiber with resistance to heat, light, and oxygen.

[0015] As the aliphatic polyamide fiber used for the reinforcing cord of the carcass ply of the pneumatic tire for passenger cars of the present invention, nylon 66 fiber or nylon 46 fiber is preferable in view of their adhesive properties at a high temperature.

[0016] When the melting point of the reinforcing cord of the carcass ply as measured by DSC is lower than 250°C, durability when used in a run-flat condition is inferior because it becomes difficult to maintain the shape of the tire at a high temperature.

[0017] The filament fiber used in the rubber-filament fiber composite which is used as a layer of a fiber reinforcing component in the present invention is not formed into twisted or woven bundles of multiple fibers like the cord fabric for tire fiber cords, and a nonwoven fabric is preferably used.

[0018] As the material of the filament fiber used in the rubber-filament fiber composite, a fiber selected from natural polymeric fibers such as cotton, rayon, and cellulose; synthetic polymeric fibers such as aromatic polyamide fibers, aliphatic polyamide fibers, polyester fibers, polyvinyl alcohol fibers, and polyimide fibers; carbon fibers; glass fibers; and steel wires may be used by themselves or in combination with any of the above fibers. Among these fibers, aromatic polyamide fibers, rayon fibers, polyethylene naphthalate fibers, polyimide fibers, carbon fibers, glass fibers, and steel wires are preferable in view of their dimensional stability at high temperatures. Specific examples of the aromatic polyamide fiber include poly-para-phenyleneterephthalamide, poly-meta-phenyleneterephthalamide, poly-para-phenyleneisophthalamide and poly-metaphenyleneisophthalamide.

[0019] The diameter or the maximum cross-sectional dimension of the filament fiber forming the rubber-filament fiber composite must be in the range of 0.0001 to 0.1 mm and is preferably in the range of 0.0001 to 0.005 mm. The length of the filament fiber forming the rubber-filament fiber composite must be 8 mm or more and is preferably 10 mm or more. When the length of the filament fiber is less than 8 mm, entanglement of filament fibers is not sufficient and the strength required as a reinforcing layer cannot be maintained.

[0020] The cross-section of the filament fiber may have a circular shape or a shape other than a circle. The filament fiber may have a hollow structure. Moreover, conjugated fibers in which different materials are used in an outer layer and in an inner layer, a radiate structure, a petal structure, or a layered structure may also be used.

[0021] It is preferable that the content of the filament fiber in the rubber-filament fiber composite is 4 to 50% by weight. When the content of the filament fiber in the rubber-filament fiber composite is less than 4% by weight, uniformity of the composite may not be able to be maintained and the rigidity required as a reinforcing layer may not be able to be exhibited. Thus, such a content is not preferable. When the content exceeds 50% by weight, the content of the continuous layer of the fiber in the rubber-filament fiber composite is large and the durability of the rubber-filament fiber composite tends to decrease thereby decreasing the durability of the tire. Thus, such a content is not preferable, either.

[0022] In the rubber-filament fiber composite comprised in the pneumatic tire for passenger cars of the present invention, it is preferable that a nonwoven fabric is used.

[0023] As the process for producing the nonwoven fabric, the needle punch process, the carding process, the melt blow process, and the spun bond process are suitable. Particularly, nonwoven fabrics obtained by the carding process in which filaments are entangled with each other by using a water stream or needles, or by the spun bond process in which filaments are entangled with each other are preferably used.

[0024] The weight per area (the weight per 1 m²) of the nonwoven fabric is preferably in the range of 10 to 300 g. When the weight per area exceeds 300 g/cm², rubber tends not to penetrate into the space inside the nonwoven fabric although the penetration may vary depending on the fluidity of the rubber and such a weight per area is not preferable in view of the separation between the fabric and the rubber in the rubber-nonwoven fabric composite when the composite is used as a component of a tire. When the weight per area is less than 10 g, uneven nonwoven fabric may be obtained because maintaining uniformity of the nonwoven fabric itself becomes difficult and a composite prepared from the nonwoven fabric and rubber may show large random variations in strength, rigidity, and elongation at break after the composite is vulcanized. Thus, such a weight per area is not preferable.

[0025] The thickness of the nonwoven fabric measured under a pressure of 20 g/cm² is preferably in the range of 0.05 to 2.0 mm and more preferably in the range of 0.1 to 0.5 mm. When the thickness of the nonwoven fabric is less than 0.05 mm, maintaining uniformity of the nonwoven fabric becomes difficult, and a composite prepared from the nonwoven fabric and rubber has insufficient strength and rigidity. When the thickness exceeds 2.0 mm, the thickness of a composite prepared from the nonwoven fabric and rubber is increased and such a material is not preferable as a component of a tire.

[0026] To form the rubber-filament fiber composite, an unvulcanized rubber composition is applied to the fiber in advance while the components remain unvulcanized. Specifically, mixing may be conducted by using any method generally used in the rubber industry, such as a method using a roll or a Banbury mixer. It is preferable from the standpoint of dispersion of the fiber that the filament fiber is added in small portions. When a nonwoven fabric is used as the filament fiber, an unvulcanized rubber composition in a sheet form is pressed to one or both faces of the nonwoven fabric by using a press or a heat roll so that the air contained inside the nonwoven fabric is sufficiently replaced with the unvulcanized rubber composition. When the fluidity of the unvulcanized rubber composition is not sufficient, it may be necessary that the unvulcanized rubber composition is pressed at an elevated temperature but still within the range where substantially vulcanization does not start. In another method, the unvulcanized rubber composition is liquefied by using a solvent and applied to the nonwoven fabric to provide the fabric with tackiness. The unvulcanized composite thus obtained is applied to prepare a green tire, which is then vulcanized in a mold.

[0027] In the formation of the composite, the filament fiber may be used without any prior adhesive treatment when the adhesion of the filament fiber to the rubber is sufficient after vulcanization. However, when the adhesion is insuffi-

cient, a dipping heat set treatment may be applied to the filament fiber in a similar manner to that used for enhancement of the adhesion between fiber cords for tires and rubber.

[0028] It is preferable that the rubber reinforcing layer having a crescent-shaped cross-section is disposed at the inner side of the carcass ply.

5 [0029] The rubber component used for the carcass ply, the rubber-filament fiber composite, and the rubber reinforcing layer is not particularly limited. Examples of the rubber component include natural rubber (NR), butadiene rubber (BR), styrene-butadiene rubber (SBR), and isoprene rubber (IR).

[0030] As for the physical properties of the rubber composition used for the composite, it is preferable that the tensile stress at 50% elongation (M_{50}) is 2 to 9 MPa and the tensile stress at 100% elongation (M_{100}) is 4 to 15 MPa.

10 [0031] The carcass ply used in the present invention can be prepared from the aliphatic polyamide cord and the rubber composition in accordance with a conventional process. The carcass ply thus prepared is applied to prepare a green tire, which is then vulcanized in a mold.

[0032] In the pneumatic tire of the present invention, the structure of the carcass, the size of the nonwoven-fabric and the position where the nonwoven fabric is disposed are not particularly limited. For example, the nonwoven-fabric can be disposed at the positions shown in Figs. .

15 [0033] The reference numbers in the figures have the following meanings:

- 1: a pneumatic tire
- 2: a side wall portion
- 20 3: a tread portion
- 4: a carcass layer
- 4a: a turned up carcass ply
- 4b: a down carcass ply
- 5: a belt portion
- 25 6: a bead core
- 7: a bead filler
- 8: a rubber reinforcing layer
- 9: a rubber-filament fiber composite
- 10: a belt reinforcing layer
- 30 11: a belt reinforcing layer

[0034] A structure of the pneumatic tire in accordance with the present invention will be described below with reference to the drawings.

35 [0035] An example of a schematic cross sectional view of the pneumatic safe tire of the present invention is shown in Fig. 1.

[0036] Both ends of a turned up carcass ply 4a using a layer of Nylon 66 in which a cord direction is directed to a radial direction of the tire 1 are turned around a pair of right and left bead core 6 and bead fillers 7. Two layers of steel belts 5 are arranged above the carcass plies 4 in a radial direction of the tire, and a tread rubber 3 is arranged in a tire road contact surface portion provided above the steel belts 5. Further, side wall rubbers 2 are arranged on the carcass layer of both sides of the tread rubber 3. In Fig. 2, belt reinforcing layers 10 and 11 are arranged outside the belt layer 5.

[0037] An arrangement of the carcass portion in the tire side portion of the pneumatic tire in the present invention is exemplified in structures I, II, III, IV and V (in Figs. 3, 4, 5, 6, and 7).

45 [0038] In the structures I and II, in addition to the two turned up carcass ply 4a using Nylon 66 cords, a reinforcing rubber layer 8 having a crescent cross section (for example, a maximum thickness 13 mm and a Shore hardness 80 degrees) is arranged inside the carcass ply 4a having a 3P carcass structure in which a sheet of down carcass 4b is arranged on the most front layer. In the structures III and IV, a reinforcing rubber layer 8 having a crescent cross section is arranged inside the carcass ply 4 having a 2P carcass structure in which an end of the carcass ply 4a using a sheet of steel cord is turned up to the tread portion enveloped structure. In the structure V, the reinforcing rubber layer 8 is arranged inside the carcass ply 4 having a 1P carcass portion in which a turned up ply forms an enveloped structure.

50 [0039] Further in structures II, IV and V, at least one sheet of rubber-filament fiber composite 9 having a specific size and composition is arranged inside the carcass ply 4a in the side wall portion.

EXAMPLES

55 [0040] The present invention is described more specifically with reference to the following examples. However, the present invention is not limited to the examples.

[0041] The melting point of the fiber was measured by a differential scanning calorimeter with a sample of about 5 mg at the speed of temperature increase of 10°C/min using a DSC manufactured by the DU PONT Company. The melting

peak temperature was taken as the melting point.

[0042] The tensile stress of the rubber composition used for the composite was measured in accordance with the method of Japanese Industrial Standard K6301-1995.

[0043] The tensile strength and the elongation at break of the reinforcing cord of the carcass ply were measured in accordance with the method of Japanese Industrial Standard L1017-1983.

[0044] Properties of the tire were measured in accordance with the following methods:

(1) Durability in a run-flat condition

[0045] A tire was attached to a rim and inflated to an internal pressure of 3.0 kg/cm². After the tire was placed in a chamber at a room temperature of 38°C for 24 hours, the core of the valve was removed to decrease the internal pressure to an atmospheric pressure. Then, the drum driving test of the tire was conducted under conditions of an applied weight of 570 kg, a speed of 89 km/hour, and a room temperature of 38°C. Durability in a run-flat condition was obtained from the driving distance at the time that the fracture occurred. Durability in a run-flat condition is shown as an index with reference to the value obtained in the control tire which is set to 100. The larger the index, the better the durability in a run-flat condition.

(2) Durability in an ordinary condition (Durability in an inflated condition)

[0046] A tire was attached to a rim and inflated to an internal pressure of 3.0 kg/cm². After the tire was placed in a chamber at a room temperature of 25°C for 24 hours, the internal pressure was adjusted again to 3.0 kg/cm². Then, the tire was pressed to a drum rotating at a circumferential speed of 60 km/hour under an applied load which was twice the load specified by the Japanese Association of Tire Manufacturers and the driving distance at the time that the fracture occurred was measured. To decide whether the tire can actually be used, the result was rated as poor (cannot be used) when the driving distance was 20,000 km or less, and as good (can be used) when the driving distance exceeded 20,000 km.

[0047] Tires of size 225/60 R16 in which a reinforcing rubber layer having a crescent-shaped cross-section was disposed at an inner side of the carcass ply of the side wall portions were prepared in accordance with the conventional process.

[0048] The formulations of the rubber compositions used for the reinforcing rubber layer are shown in Table 1.

Table 1

	parts by weight
natural rubber	30
butadiene rubber* ¹	70
carbon black* ²	60
softener* ³	5.0
zinc oxide	3.0
stearic acid	1.0
antioxidant* ⁴	2.0
vulcanization accelerator* ⁵	3.5
sulfur	5.0

*1 BR01 (trademark, manufactured by JSR Corporation)

*2: FEF

*3: Spindle oil

*4: NOCRAC 6C (trademark, manufactured by OUCHI SHINKO KAGAKU KOGYO Co., Ltd.)

*5: NOCELER NS (trademark, manufactured by OUCHI SHINKO KAGAKU KOGYO Co., Ltd.)

[0049] Rubber-filament fiber composites were prepared as follows: When a nonwoven fabric was not used as the fil-

EP 0 924 109 A2

ament fiber, a rubber-filament fiber composite was prepared by using a Banbury mixer. When a nonwoven fabric was used as the filament fiber, an unvulcanized rubber composition in a sheet form was pressed to both faces of the nonwoven fabric by a press at 70°C.

[0050] The rubber composition used was the same as that used for the reinforcing rubber layer.

5 [0051] The following four types of carcass structure were examined:

Structure I: A 3P structure having two turned-up carcass plies and one down carcass ply at an outer side of the turned-up plies.

10 Structure II: A 3P structure having two turned-up carcass plies, one down carcass ply at an outer side of the turned-up plies and a rubber-filament fiber composite disposed at an inner side of a rubber reinforcing layer having a crescent-shaped cross-section.

Structure III: A 2P structure having one turned-up carcass ply and one carcass ply whose end is turned up to a tread portion.

15 Structure IV: A 2P structure having one turned-up carcass ply, one carcass ply whose end is turned up to a tread portion, and a rubber-filament fiber composite disposed at an inner side of a rubber reinforcing layer having a crescent-shaped cross-section.

Structure V: A 1P structure having carcass ply whose end is turned up to a tread portion, and a rubber-filament fiber composite disposed at an inner side of a rubber reinforcing layer having a crescent-shaped cross-section.

20 [0052] For the reinforcing cord of the carcass ply, nylon 66 fiber (melting point: 260°C) or nylon 46 fiber (melting point: 290°C) was used.

[0053] The structure of the tires and the results of the evaluation of the properties of the tires are shown in Table 2.

Table 2 - 1

	Comparative Example 1	Example 1	Example 2	Example 3
Reinforcing component				
reinforcing rubber layer	present	present	present	present
30 composite				
nonwoven fabric	absent	present	present	absent
filament fiber	absent	absent	absent	present
35 fiber	-	aramide	aramide	aramide
length of fiber (mm)	-	50	50	50
diameter of fiber (mm)	-	0.02	0.02	0.02
weight per area (g/m ²)	-	50	50	-
40 Carcass ply cord				
material	nylon 66	nylon 66	nylon 46	nylon 66
structure	1400dtex/2	1400dtex/2	1400dtex/2	1400dtex/2
45 tensile strength (N/cord)	230	230	224	230
elongation at break (%)	20.0	20.0	15.0	20.0
structure	3P	3P	3P	3P
50 Tire structure	I	II	II	II
Durability in a run-flat condition (index)* ¹	100	125	130	125
Durability in an inflated condition	good	good	good	good

*1.: Comparative Example 1 is the control run for Examples 1 to 3.

Table 2 - 2

	Comparative Example 2	Example 4	Example 5
Reinforcing component			
reinforcing rubber layer	present	present	present
composite			
nonwoven fabric	absent	present	present
filament fiber	absent	absent	absent
fiber	-	aramide	aramide
length of fiber (mm)	-	50	50
diameter of fiber (mm)	-	0.02	0.02
weight per area (g/m ²)	-	50	50
Carcass ply cord			
material	nylon 66	nylon 66	nylon 46
structure	1400dtex/2	1400dtex/2	1400dtex/2
tensile strength (N/cord)	230	230	224
elongation at break (%)	20.0	20.0	15.0
structure	2P	2P	2P
Tire structure	III	IV	IV
Durability in a run-flat condition (index)* ¹	100	130	135
Durability in an inflated condition	good	good	good

*1: Comparative Example 2 is the control run for Examples 4 and 5.

[0054] It is shown that durability of a tire can be improved by disposing a rubber-filament fiber composite at side wall portions in all structures of the carcass plies.

[0055] In accordance with the present invention, a pneumatic tire for passenger cars showing excellent durability is provided because deterioration of adhesion in carcass ply does not take place during use, particularly during use in a run-flat condition.

Claims

1. A pneumatic tire for passenger cars comprising:

a pair of left and right ring-shaped bead cores;
 a carcass layer formed from a layer in which a plurality of reinforcing cords disposed substantially parallel to each other are embedded in a covering rubber;
 a tread portion disposed at an outer side of said carcass portion in the radial direction of the tire; and
 a pair of side wall portions disposed at the left and right of said tread portion;
 wherein a rubber reinforcing layer having a crescent-shaped cross-section and at least one sheet of a rubber-filament fiber composite having a thickness of 0.05 to 2.0 mm which is formed from a rubber component and filament fibers having a diameter or a maximum cross-sectional dimension of 0.0001 to 0.1 mm and a length of 8 mm or more are disposed in said side wall portions; and
 said reinforcing cords of carcass plies are made of an aliphatic polyamide fiber having a melting point of 250°C or higher as measured by DSC.

2. A pneumatic tire according to Claim 1, wherein said filament fiber in said rubber-filament fiber composite is at least one fiber selected from the group consisting of aromatic polyamide fiber, rayon fiber, polyethylene naphthalate fiber, polyimide fiber, carbon fiber, glass fiber and steel wire.

EP 0 924 109 A2

3. A pneumatic tire according to Claim 1, wherein said filament fiber in said rubber-filament fiber composite has a diameter or a maximum cross-sectional dimension of 0.0001 to 0.005 mm and a length of 10 mm or more.
4. A pneumatic tire according to Claim 1, wherein the content of the filament fiber in said rubber-filament fiber composite is 4 to 50% by weight.
5. A pneumatic tire according to Claim 1, wherein said rubber-filament fiber composite is formed from a rubber and a nonwoven fabric having a weight per area of 10 to 300 g/m².
6. A pneumatic tire according to Claim 5, wherein said nonwoven fabric has a thickness measured under a pressure of 20 g/cm² of 0.1 to 0.5 mm.
7. A pneumatic tire according to Claim 1, wherein said reinforcing cords of carcass plies are made of at least one fiber selected from the group consisting of nylon 66 fiber and nylon 46 fiber.

FIG. 1




FIG. 2






FIG. 3



STRUCTURE 1

FIG. 4



STRUCTURE II

FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15






FIG. 16





Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 924 109 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
03.11.1999 Bulletin 1999/44

(51) Int. Cl.⁶: **B60C 17/00**, B60C 9/14,
B60C 9/00

(43) Date of publication A2:
23.06.1999 Bulletin 1999/25

(21) Application number: 98310603.0

(22) Date of filing: 22.12.1998

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 22.12.1997 JP 35376697


(71) Applicant:
BRIDGESTONE CORPORATION
Tokyo 104-0031 (JP)

(72) Inventors:
• Nishikawa, Tomohisa,
c/o Bridgestone Corporation
Chuo-ku, Tokyo 104-0031 (JP)
• Matsuo, Kenji,
c/o Bridgestone Corporation
Chuo-ku, Tokyo 104-0031 (JP)
• Kobayashi, Kazuomi,
C/o Bridgestone Corporation
Chuo-ku, Tokyo 104-0031 (JP)

(74) Representative: Whalley, Kevin
MARKS & CLERK,
57-60 Lincoln's Inn Fields
London WC2A 3LS (GB)

(54) Pneumatic tire for passenger cars

(57) The present invention provides a pneumatic tire for passenger cars comprising bead cores, a carcass layer, a tread portion, and side wall portions, wherein a rubber reinforcing layer having a crescent-shaped cross-section and at least one sheet of a rubber-filament fiber composite having a thickness measured under a pressure of 20 g/cm² of 0.05 to 2.0 mm which is formed from a rubber component and filaments having a diameter or a maximum cross-sectional dimension of 0.0001 to 0.1 mm and a length of 8 mm or more are disposed in said side wall portions and reinforcing cords of carcass plies are made of an aliphatic polyamide fiber having a melting point of 250°C or higher. Deterioration of adhesion in carcass ply does not take place during use, particularly during use in a run-flat condition, and the pneumatic tire shows excellent durability.



EP 0 924 109 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 31 0603

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
Y	US 4 067 372 A (MASSON YVES) 10 January 1978 (1978-01-10) * column 2, line 46 - line 65; claims; figures * ---	1-4,7	B60C17/00 B60C9/14 B60C9/00 B60C9/12
Y	US 5 217 549 A (JOHNSON DAVID A) 8 June 1993 (1993-06-08) * column 6, line 12 - line 23; claims; figures * * column 1, line 31 - line 63 * ---	1-4,7	
P,A	WO 98 54011 A (KINOSHITA KATSUHIKO ;KOBAYASHI KAZUOMI (JP); ITO SHUNGO (JP); MATS) 3 December 1998 (1998-12-03) * claims; figures * ---	1-7	
A	EP 0 613 795 A (SUMITOMO RUBBER IND) 7 September 1994 (1994-09-07) * claims * ---	1	
P,A	WO 98 54008 A (BROYLES HENRY DAVID ;BEER KLAUS (US); PRAKASH AMIT (US); TUBB GARY) 3 December 1998 (1998-12-03) ---	1	TECHNICAL FIELDS SEARCHED (Int.Cl.6) B60C
P,A	PATENT ABSTRACTS OF JAPAN vol. 098, no. 006, 30 April 1998 (1998-04-30) & JP 10 053012 A (BRIDGESTONE CORP), 24 February 1998 (1998-02-24) * abstract * ---	1	
A	US 4 121 641 A (NAKASAKI EIJI) 24 October 1978 (1978-10-24) * column 2, line 4 - line 8 * * column 4, line 61 - column 5, line 36; claims; figures * --- -/--	1,5,6	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 16 September 1999	Examiner Baradat, J-L
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons S : member of the same patent family, corresponding document	

EPO FORM 1503 03 82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 31 0603

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	PATENT ABSTRACTS OF JAPAN vol. 097, no. 007, 31 July 1997 (1997-07-31) & JP 09 058229 A (YOKOHAMA RUBBER CO LTD:THE), 4 March 1997 (1997-03-04) * abstract *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 16 September 1999	Examiner Baradat, J-L
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 02 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 31 0603

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-09-1999

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4067372	A	10-01-1978	FR 2261888 A	19-09-1975
			AT 340253 B	12-12-1977
			AT 144075 A	15-03-1977
			AU 7859675 A	26-08-1976
			BE 826014 A	26-08-1975
			CA 1001936 A	21-12-1976
			CH 591965 A	14-10-1977
			DE 2508360 A	28-08-1975
			GB 1495588 A	21-12-1977
			IT 1030222 B	30-03-1979
			JP 50152403 A	08-12-1975
			SE 415336 B	29-09-1980
			SE 7502119 A	27-08-1975
US 5217549	A	08-06-1993	CA 2064937 A,C	05-10-1992
			DE 69205610 D	30-11-1995
			DE 69205610 T	11-04-1996
			EP 0507184 A	07-10-1992
			ES 2078572 T	16-12-1995
			JP 5112110 A	07-05-1993
WO 9854011	A	03-12-1998	JP 10053012 A	24-02-1998
			EP 0922593 A	16-06-1999
EP 0613795	A	07-09-1994	DE 69403117 D	19-06-1997
			DE 69403117 T	28-08-1997
			JP 7032828 A	03-02-1995
WO 9854008	A	03-12-1998	US 5871600 A	16-02-1999
			US 5871602 A	16-02-1999
			AU 6560698 A	30-12-1998
			AU 6943398 A	30-12-1998
			AU 7124998 A	30-12-1998
			AU 7693298 A	30-12-1998
			WO 9854007 A	03-12-1998
			WO 9854012 A	03-12-1998
			WO 9854014 A	03-12-1998
			AU 7125098 A	30-12-1998
			WO 9854013 A	03-12-1998
			AU 7250798 A	30-12-1998
			WO 9854010 A	03-12-1998
JP 10053012	A	24-02-1998	EP 0922593 A	16-06-1999
			WO 9854011 A	03-12-1998
US 4121641	A	24-10-1978	JP 934530 C	30-11-1978

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 98 31 0603

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-09-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4121641 A		JP 52066203 A	01-06-1977
		JP 53014801 B	20-05-1978
JP 09058229 A	04-03-1997	NONE	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82